

TECHNICAL DATA SHEET

10130DSC13X55 / #11162



GORI 55 SENSITIVE Wood Finish

GORI 55 SENSITIVE is a decorative, weatherproof, opaque wood finish. Offers long term protection. Forms a hardwearing, elastic film. Tested according to DIN EN71, Part 3 (safe to use on children's toys). For test certificate, see www.gori.com.



PRODUCT DESCRIPTION

Where to use	All types of exterior and interior wood. Can also be used on pre-treated aluminium, galvanised and primed steel surfaces and UPVC surfaces.
Form supplied	Ready to use.
Substrate	The surface must be clean, dry and solid.
Pre-treatment	<u>Exterior wood</u> : Untreated soft wood: 1 coat of a GORI wood preservative. Hardwood: no pre-treatment needed. <u>Interior wood</u> : no pre-treatment needed.
Treatment	Read label and instructions before use. Stir product well before use. Apply 2-3 coats of GORI 55. Close can firmly after use. <u>Maintenance</u> : Sand down badly weathered surfaces to sound wood. Remove oil, grease and loose particles and apply 1-2 coats of GORI 55.
Application method	Apply with brush or roller. Do not apply in direct sunlight. During application and drying, temperature must be above 5°C and relative humidity below 80%.
Thinning	Do not thin.

TECHNICAL DATA SHEET

10130DSC13X55 / #11162



Cleaning of tools Soap and water.

General Mix different batches to avoid variations in colour and gloss.

TECHNICAL PRODUCT DESCRIPTION

Odour Weak. Odourless after drying.

Coverage App. 10 m²/l – depending on the state of the substrate.

Drying time Touch dry: app. 1 hour. Recoatable: app. 12 hours. Fully cured: app. 48 hours. Wait 48 hours before closing coated window frames. Measured at 23°C and normal humidity (60%). Deviations may occur depending on temperature, humidity, ventilation conditions and layer thickness.

Shelf life 3 years in unopened container. Limited shelf life after opening.

Storage Store and transport frost free in tightly closed container. Store in a dry and cool area away from direct sunlight.

TECHNICAL DATA

Product type Acrylic dispersion for wood.

Density App. 1.2 g/ml.

Flash point Not flammable.

Solid content 31.5-36.8 vol %.

Viscosity Creamy (E1 64-70).

Gloss Silky.

COMPOSITION

Binder 100% acrylate.

Solvent Water

Pigments Organic and inorganic.

Active ingredients None.

TECHNICAL DATA SHEET

10130DSC13X55 / #11162



SAFETY AND ENVIRONMENT

General

Please observe common safety rules for work with paints and varnishes. Further information is available from our safety data sheet on: www.gori.com.

Disposal

Do not empty into drains or into the environment. Do not pour product waste into sewers, water reserves or soil. Hand in left over product at your local waste disposal. Empty may be recycled (check with your local waste disposal site or your local authorities).

ADDITIONAL INFORMATION

Wood species

Western Red Cedar, Alaska Yellow Cedar, Larch and similar types of wood contain tannin, which may repel coating and/or staining. Please make a test on a small area before treating and check the result.

Please also note that all softwood may retract or swell up to 12 %. No film can adapt to this kind of movement and therefore a maximum of 18 % humidity is the limit for applying treatment.

Iroko, Teak, Rubber wood and some other wood species contain "oil", which may delay drying and thereby give an uneven surface after application. You can try cleaning the surface with cellulose thinner and then sand with grit 220. Then apply GORI 55 on a small test area. We stress that there is no guarantee for a satisfactory result.

As wood is an organic material, there is no guarantee that the same wood species will react the same way in different areas, when treated/coated/stained. For more information and safety data sheets: www.gori.com.

The purpose of this Technical Data Sheet is to provide our clients with information about the properties and characteristics of the product. The information provided is based on tests conducted by us under usage conditions that comply with the prevailing standards. Our recommendations for use are for information only, and in no event shall they take precedence over any specific recommendation taking into account the nature and conditions of a particular site, nor shall they engage PPG's liability. Before all applications of the product, clients should check that this document has not been amended by a more recent version, which takes into account new technical data. This version annuls and replaces all previous versions of Technical Data Sheets relating to this product. Technical Data Sheets can be downloaded from www.gori.com.

PPG Coatings Danmark A/S
Gladsaxevej 300
DK-2860 Søborg
Tel: +45 39 57 93 00
export@ppg.com
www.gori.com